



BCTC
CARPET TECHNICAL CENTRE

Confidential Report

Our Ref: 26/01735B/04/14

Notified Body
for PPE Directive,
Construction Products
Regulation & Marine
Equipment Directive
I.D. No. 0338 & 0339

**British Carpet Technical Centre
Wira House, West Park Ring Road,
Leeds, LS16 6QL**

Tel No: +44 (0)113 25919969 Fax No: +44 (0)113 2780306



BCTC

CARPET TECHNICAL CENTRE

British Carpet Technical Centre
Wira House
West Park Ring Road
Leeds, LS16 6QL
England

Tel: +44 (0)113 259 1999
Fax: +44 (0)113 278 0306
Web: <http://www.bttg.co.uk>
Email: CSLeeds@bttg.co.uk

8 May 2014

Our Ref: 26/01735B/04/14
Your Ref:

Page 1 of 2

Client: Soyang Europe Ltd
Unit 38
Peel Industrial Estate
Bury
Lancashire
BL9 0LU

Job Title: **Coefficient of Friction Test on One Sample of Flooring**

Clients Order Ref: --

Date of Receipt: 16 April 2014

Description of Sample: One sample of flooring, referenced: **G Floor**.

Work Requested: BCTC were requested to carry out a Coefficient of Friction Test on the sample of flooring supplied.



BCTC
CARPET TECHNICAL CENTRE

British Carpet Technical Centre.
Wira House
West Park Ring Road
Leeds, LS16 6QL
England

Tel: +44 (0)113 259 1999
Fax: +44 (0)113 278 0306
Web: <http://www.bttg.co.uk>
Email: CSLeeds@bttg.co.uk

8 May 2014

Page 2 of 2

Our Ref: 26/01735B/04/14
Your Ref:

Soyang Europe Ltd

Determination of Coefficient of Friction


The coefficient of friction was determined in dry and wet conditions, in the direction of manufacture using the TRRL Pendulum Tester with a 4s rubber slider. The sample was subjected to eight measurements in both conditions, in accordance with BS 7976-2: 2002. The mean pendulum test value was calculated over the last five measurements.


<u>Area No.</u>	<u>Coefficient of Friction</u>	
	<u>Dry</u>	<u>Wet</u>
1	60	40
2	65	40
3	65	45
4	60	40
5	65	45
Mean	63	43

Note

The United Kingdom Slip Resistance Group guidelines are as follows:-

High Slip Potential: 0 – 24
Moderate Slip Potential: 25 – 35
Low Slip Potential: 36+

Reported by:.....  K Pillinger, Laboratory Technician

Countersigned by:.....  P Doherty, Operational Head

Enquiries concerning this report should be addressed to Customer Services.